



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 013 724 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
28.06.2000 Bulletin 2000/26

(51) Int. Cl.⁷: C09C 1/00, C09D 11/02

(21) Application number: 99125928.4

(22) Date of filing: 23.12.1999

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: 23.12.1998 EP 98124473

(71) Applicant: MERCK PATENT GmbH
64293 Darmstadt (DE)

(72) Inventors:
• Pfaff, Gerhard, Dr.
64839 Münster (DE)
• Schoen, Sabine, Dr.
64287 Darmstadt (DE)
• Nishimagi, Atsuko
Takijiri, Fukushima-pref, 971-8182 (JP)

(54) **Pigment mixture**

(57) The present invention relates to pigment mixtures containing at least two components, component A being Al₂O₃ flakes coated with one or more metals, metal oxides and/or metal sulfides and component B being special-effect pigments, and to their use in varnishes, paints, printing inks, masterbatches, plastics and cosmetic formulations.

EP 1 013 724 A1

Description

[0001] The present invention relates to pigment mixtures containing at least two components, component A being Al_2O_3 flakes coated with one or more metals, metal oxides and/or metal sulfides and component B being special-effect pigments, and to their use in varnishes, paints, printing inks, plastics and cosmetic formulations.

[0002] With platelet-shaped pigments, hiding power and gloss are often difficult to realise simultaneously to a satisfactory extent. For instance, SiO_2 flakes or mica platelets covered with one or more thin metal oxide layers feature interference colours and a high lustre but at the same time, owing to the transparent substrate, feature high transparency and hence a comparatively poor hiding power.

[0003] Thus EP 0 562 329 discloses a pigment mixture comprising iron oxide-coated SiO_2 flakes in combination with iron oxide-coated mica pigments.

[0004] DE-A-42 40 511 discloses a pigment mixture which consists of an interference pigment and a platelet-shaped colour pigment. The interference pigment comprises metal oxide-coated mica flakes or SiO_2 flakes, and the colour pigment can be coloured, uncoated SiO_2 flakes. This pigment mixture is incorporated into coating materials, printing inks or plastics.

[0005] The object of the present invention is to provide a pigment mixture which is notable for relatively high hiding power and which lends itself well to incorporation into the respective system in which it is used, and for which at the same time a separation of pigment/colourant in the system is largely ruled out.

[0006] Surprisingly, a pigment mixture has now been found which has none of the disadvantages indicated above. The pigment mixture of the invention consists of at least two components, component A being Al_2O_3 flakes coated with one or more metals, metal oxides and/or metal sulfides and component B being one or more special-effect pigments. The admixture of the special-effect pigments to the coated Al_2O_3 flakes is able to give the systems in which they are used a multiple flop, the colour effect is intensified, and new colour effects are achieved.

[0007] The invention thus provides a pigment mixture containing at least two components, component A being Al_2O_3 flakes coated with one or more metals, metal oxides and/or metal sulfides and component B being one or more special-effect pigments.

[0008] The invention likewise provides the formulations, such as paints, varnishes, printing inks, plastics, agricultural films and cosmetic formulations, which comprise the pigment mixture of the invention.

[0009] The coated Al_2O_3 flakes can be mixed in any proportion with the special-effect pigments. The ratio of component A to component B is preferably from 1:10 to 10:1, in particular from 3:1 to 5:1.

[0010] Coated aluminum oxide in a flaky form is

commercial available for example from Merck KGaA under the tradename Xirallic®.

[0011] $\alpha\text{-Al}_2\text{O}_3$ in the form of hexagonal flakes having a particle diameter greater than 10 μm and an aspect ratio (particle diameter/thickness) of 5-10 is known from JP 111239/1982 (Laid Open No.).

[0012] The Japanese Patent Publication No. 72527/1991 discloses $\alpha\text{-Al}_2\text{O}_3$ in the form of flakes having an average particle diameter of 0.5-3 μm .

[0013] The JP 39362/1992 (Laid Open No.) describes Al_2O_3 in the form of fine platy particles of a hexagonal crystal system with the plane perpendicular to the c axis grown into a plate.

[0014] Preferred Al_2O_3 flakes are flakes composed of aluminum oxide (as a major constituent) and of titanium dioxide (as a minor constituent) which are known from U.S. 5,702,519. These Al_2O_3 flakes are prepared from a uniform aqueous solution water-soluble aluminum salt and titanium salt by hydrolysis with an alkali carbonate aqueous solution in the presence of an aqueous solution containing an alkali metal salt like alkali metal sulfate and phosphoric acid or phosphate, drying by evaporation (dehydration by heating), and molten salt treatment.

[0015] The Al_2O_3 flakes are provided with one or more metal oxide layers. Examples of suitable metal oxides or metal oxide mixtures are titanium dioxide, zirconium oxide, zinc oxide, iron oxides (Fe_2O_3 and/or Fe_3O_4) and/or chromium oxide, especially TiO_2 and/or Fe_2O_3 . The Al_2O_3 flakes can be coated in the same way as pearl lustre pigments. Coatings with a metal oxide may be accomplished by any known methods, such as hydrolysis of a metal salt by heating or alkali, which deposits hydrated metal oxide, followed by calcination.

[0016] Al_2O_3 flakes can also be coated with one or more layers of a metal or metal alloy selected e.g. from chromium, nickel, silver, bismuth, copper, tin, or hastalloy. Al_2O_3 flakes coated with a metal sulfide are coated with sulfides e.g. of tungsten, molybdenum, cerium, lanthanum or rare earth elements.

[0017] The Al_2O_3 flakes can be coated by wet chemical coating, by CVD or PVD processes.

[0018] Suitable components B for the pigment mixture of the invention are all special-effect pigments familiar to the skilled worker in the effect pigment sector, examples being metal effect pigments, such as aluminum, copper, zinc, tin and their alloys. Aluminum and gold bronze alloys are preferably to be mentioned, especially those having a particle size of 2 to 40 μm .

[0019] The pigment mixtures of the invention preferably comprise uncoated and coated platelet-shaped iron oxide, aluminum flakes or coated aluminum flakes. Special-effect pigments of this kind are marketed by BASF under the name Paliocrom®, by Eckart-Werke under the name Stapa®, and by the Flex Company under the name ChromaFlair®. The following pigments should also be mentioned: Pearl lustre pigments, TiO_2 flakes or SiO_2 flakes coated with one or more metal

oxides, such as TiO_2 or Fe_2O_3 , for example, graphite platelets, BiOCl or glass flakes coated with one or more metal oxides, liquid crystal polymer particles (LCP), holographic pigments and multilayer pigments.

[0020] Pearl lustre pigments, mica flake pigments coated with one or more metal oxides, are obtainable, for example, from Merck KGaA, Darmstadt, under the tradenames Iriodin®, Afflair® and Timiron®. The latter pigments are known, for example, from the German Patents and Patent Applications 14 67 468, 19 59 998, 20 09 566, 22 14 545, 22 15 191, 22 44 298, 23 13 331, 25 22 572, 31 37 808, 31 37 809, 31 51 343, 31 51 354, 31 51 355, 32 11 602 and 32 53 017. Mica pigments coated with TiO_2 and/or Fe_2O_3 are employed in particular. As phyllosilicate both natural and synthetic mica are suitable.

[0021] Additionally, the inventive pigment mixture can contain organic or inorganic colourants, thixotropic agents, wetting agents, dispersing agents, water, organic solvent or solvent mixtures, etc.

[0022] The pigment mixture of the invention is simple and easy to handle. The pigment mixture can be incorporated into the system in which it is used by simple stirring. Laborious milling and dispersing of the pigments is not necessary.

[0023] The pigment mixture of the invention can be used for pigmenting coating materials, printing inks, plastics, agricultural films, button pastes, for the coating of seed, for the colouring of food, coatings of medications or cosmetic formulations. The concentration of the pigment mixture in the system in which it is to be used for pigmenting is generally between 0.01 and 50 % by weight, preferably between 0.1 and 5 % by weight, based on the overall solids content of the system. This concentration is generally dependent on the specific application.

[0024] Plastics comprising the pigment mixture of the invention in amounts of 0.1 to 50 % by weight, in particular from 0.5 to 7 % by weight, are frequently notable for a particular sparkle effect.

[0025] In the coating sector, especially in automotive finishing, the pigment mixture is employed in amounts of 0.5-10 % by weight. The proportion in which the coated Al_2O_3 flakes are mixed with component B, especially coated SiO_2 flakes or coated mica platelets, depends on the desired effect. The Al_2O_3 flakes are preferably employed with component B in a ratio of 1:10 to 10:1, in particular of 3:1.

[0026] In the coating material, the pigment mixture of the invention has the advantage that the desired colour flop effect is obtained by a single-layer coating (one-coat systems or as a base coat in a two-coat system). This colour flop is extremely pronounced even under diffuse light. In comparison with coatings which comprise an interference pigment rather than the coated Al_2O_3 flakes, coatings with the pigment mixture of the invention exhibit a marked depth effect and a glitter effect and also a strong colour flop.

[0027] In the pigmentation of binder systems, for example for paints and printing inks for intaglio, offset or screen printing, pigment mixtures consisting of coated Al_2O_3 flakes with Stapa®-aluminum and gold bronze pastes from Eckart-Werke have proven particularly suitable. The pigment mixture is incorporated into the printing ink in amounts of 2-50 % by weight, preferably 5-30 % by weight and, in particular, 8-15 % by weight. The mixing ratio of component A to component B is preferably in the range from 1:10 to 10:1. The printing inks comprising the pigment mixture of the invention exhibit purer hues and are of improved printability owing to the good viscosity values.

[0028] The invention likewise provides pigment preparations comprising coated Al_2O_3 flakes, effect pigments, binders and, if desired, additives, the said preparations being in the form of substantially solvent-free, free-flowing granules. Such granules contain up to 95 % by weight of the pigment mixture. A pigment preparation in which the pigment mixture of the invention is pasted up with a binder and with water and/or an organic solvent, with or without additives, and the paste is subsequently dried and brought into a compact particulate form, e.g. granules, pellets, briquettes, a masterbatch or tablets, is particularly suitable as a precursor for printing inks.

[0029] The present invention therefore also provides formulations containing the pigment mixture of the invention.

[0030] The examples which follow are intended to illustrate the invention without, however, limiting it.

Examples

Example 1: Paint

[0031] Formulations consisting of

2.50 %	Fe_2O_3 -coated Al_2O_3 flakes having a particle size of 5-60 μm (Merck KGaA)
1.50 %	Monastral green 6Y spec. (Zeneca)
0.50 %	Cappoxyt yellow 4214 (Capelle)
0.03 %	Pigment-grade carbon black FW 200 (Degussa)
0.40 %	Dollaraluminum Alplate 7620 NS (Alcan Toyo Europe)
Remainder:	Paint base with 19 % solids content (acrylate-melamine) and diluent mixture

Example 2: Intaglio printing

[0032] Printing ink consisting of

70 g	nitrocellulose-based binder from Gebrüder Schmidt, 95MB011, with solids content of about 20 %
30 g	pigment, i.e. 15 g of Cromal IV (Eckart) AL 14-18 μm and 15 g of Fe_2O_3 -coated Al_2O_3 flakes

of particle size 5-60 μm
30 g 1-ethoxy-2-propanol

ad 100.00 % Aqua

Phase B

Example 3: Plastic

[0033] 1 kg of polystyrene granules are wetted uniformly in a tumble mixer with 5 g of adhesion agent. Then 35 g of Fe_2O_3 -coated Al_2O_3 flakes of particle size 5-60 μm and 7g of Iriodin® 121 (TiO_2 -coated mica pigment from Merck KGaA, Darmstadt, FRG with particle size 5-20 μm) are added and the components are mixed for 2 minutes.

[0034] These granules are processed under customary conditions on an injection moulding machine to give small stepped plates measuring 4 x 3 x 0.5 cm. The small stepped plates are notable for their lustre.

Example 4: Eye shadow

Phase A

[0035]

15.00 % TiO_2 -coated Al_2O_3 flakes of particle size 5-60 μm (Merck KGaA)
15.00 % Timiron® Super Blue (TiO_2 -coated mica of particle size 10-60 μm from Merck KGaA)
49.50 % Talc
7.50 % Solanum Tuberosum (potato starch)
2.50 % Magnesium stearate

Phase B

[0036]

9.14% Isopropyl stearate
0.53 % Cetyl palmitate
0.53 % Petrolatum
0.21 % Fragrance
0.11 % Preservative

[0037] The constituents of Phase A are combined and formed into a premix. The melted phase B is then added dropwise with stirring to the powder mixture. The powders are pressed at 40-50 bar.

Example 5: Shower gel

Phase A

[0038]

0.10 % TiO_2 -coated Al_2O_3 flakes of particle size 5-60 μm (Merck KGaA)
0.10 % Timiron® Super Blue (TiO_2 -coated mica of particle size 10-60 μm from Merck KGaA)
0.75 % Xanthan gum

5 [0039]

20.00 % Decyl glycoside
6.65 % Texapon ASV Sodium laureth sulfate Magnesium laureth sulfate Sodium laureth 8-sulfate Magnesium laureth 8-sulfate Sodium oleth sulfate
0.20 % Preservative
0.50 % Fragrance

15 Phase C

[0040]

0.15 % Citric acid
20 10.00% Aqua

[0041] For Phase A, the pigments are stirred into the water. The xanthan gum is scattered in slowly with stirring and the mixture is stirred until the gum has dissolved. Phases B and C are added in succession, and slow stirring is continued until all of the components are homogeneously distributed.

Claims

1. Pigment mixture containing at least two components, component A being Al_2O_3 flakes coated with one or more metals, metal oxides and/or metal sulfides and component B being special-effect pigments.
2. Pigment mixture according to Claim 1, characterised in that component A comprises TiO_2 - and/or Fe_2O_3 -coated Al_2O_3 flakes.
3. Pigment mixture according to Claim 1 or 2, characterised in that component B comprises metal platelets coated with one or more metal oxides, graphite platelets, aluminum platelets, phyllosilicates, Fe_2O_3 -, SiO_2 -, or TiO_2 -flakes uncoated or coated with one or more metal oxides, glass platelets and/or ceramic platelets.
4. Pigment mixture according to one of Claims 1 to 3, characterised in that component A and component B are mixed in a ratio of 10:1 to 1:10.
5. Use of the pigment mixture according to Claim 1 in paints, varnishes, printing inks, powder coating materials, master batches, plastics, for colouring seed, in cosmetic formulations and for enhancing foods.

6. Formulations containing a pigment mixture according to Claim 1.
7. Pigment preparation containing a pigment mixture according to Claim 1 and a binder, characterised in that it is in the form of substantially solvent-free, free-flowing granules.

10

15

20

25

30

35

40

45

50

55



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 99 12 5928

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X,P	DE 198 20 112 A (ECKART-WERKE) 11 November 1999 (1999-11-11) * the whole document * * page 2, line 62 - page 3, line 2; claims 6,7 *	1-3,5-7	C09C1/00 C09D11/02
A,D	EP 0 763 573 A (MERCK PATENT GMBH) 19 March 1997 (1997-03-19) * the whole document *	1-7	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			C09C C09D
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 29 February 2000	Examiner Luethe, H
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 D9.92 (P04001)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 99 12 5928

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

29-02-2000

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DE 19820112 A	11-11-1999	WO 9957204 A	11-11-1999
EP 763573 A	19-03-1997	JP 9077512 A	25-03-1997
		CN 1150165 A	21-05-1997
		US 5702519 A	30-12-1997

EPO FORM P/488

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82